Product Information Sheet



Saffil Blanket

Description

Saffil Blankets are high temperature, lightweight, needled blankets manufactured from high purity polycrystalline wool with a polypropylene carrier to optimise strength and flexibility. Designed for use up to 1600°C, Saffil Blankets can be used in a wide variety of applications. They are especially suited to environments where the presence of 'shot' (unfiberised particles) is undesirable or where resistance to corrosive agents is essential.

General Characteristics

Saffil Blanket has the following outstanding characteristics:

- High temperature stability (up to 1600°C)
- Low thermal conductivity
- Virtually 'shot' free
- · Resistance to thermal shock & chemical attack
- · High tensile strength & resiliency
- · Insoluble in water
- · Suited to veneer and anchored modules



Typical Applications

- · High temperature furnace, boiler & kiln linings
 - · Blast, forging, re-heat & heat treatment
 - · Ethylene, catalyst & sulphur heaters and reformers
 - · Porcelain, refractory, laboratory & dental kilns
- Speciality applications
 - · Acoustic insulation
 - Semiconductor processing & fuel cell components



Typical Product Parameters

Saffil Blanket		
Typical Chemical Analysis (fibre wt. %)		
Al ₂ O ₃	95 – 97	
SiO ₂	3 – 5	
Trace	<0.5	
Physical Properties		
Colour	White	
Classification Temperature (°C)*	1600	
Loss on Ignition (wt. %)		
from Fibre	0	
from Blanket+	<5	
Median Fibre Diameter (microns)	3 – 4	
Product Density (kg/m³)	96	
Specific Heat at 1000°C (J/kgK)	1000	
Thermal Conductivity (W/mK)		
Mean Temp.		
800°C	0.16	
1000°C	0.23	
1200°C	0.32	
Permanent Linear Shrinkage (%) 6 Hour Soak		
1500°C	<4	

^{*}Classification Temperature is not a definition of the operational limit of these products, especially when long term physical or dimensional stability is a factor. For certain applications, continuous use temperature limits may be significantly reduced. For assistance or clarification, please contact your nearest Unifrax Engineering office.

Availability

Thickness (mm)	Roll Width (mm)	Roll Length (m)
13	610	14.4
25	610	7.2

All product dimensions provided are nominal dimensions.

Handling Information

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

The following is a registered trademark of Unifrax I LLC: Saffil.

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.

Form U-412 EN Effective 9/18 © 2018 Unifrax I LLC All Rights Reserved Page 2 of 2



Unifrax I LLC

European Sales & Marketing Headquarters Unifrax Limited Mill Lane, Rainford, St. Helens, Merseyside England, WA11 8LP

Telephone: +44 (0)1744 88 7600 Internet: www.unifrax.com Email: info@unifrax.com

^{*}Upon initial firing of the blanket, a small amount of organic burnout will occur due to the polypropylene carrier.