

Data sheet

Superwool® Papers

ENGLISH

Metric/Imperial information - Page 2

Packaging information - Page 3

Description

Superwool papers are uniquely designed from Superwool bulk and organic binders. Superwool papers are specially processed to offer excellent performance in high-temperature applications. Superwool papers offer an alternative to traditional solutions due to its unique properties of high refractoriness and excellent non-wetting characteristics to applications requiring direct contact with molten aluminium.

Superwool provides stability and resistance to chemical attack. Exceptions include hydrofluoric acid, phosphoric acid and strong alkalis (i.e. NaOH, KOH). Superwool is unaffected by incidental spills of oil or water. Thermal and physical properties are restored after drying.

Superwool Flex-Wrap is produced from a blend of Superwool high purity fibers and organic binders. Due to its low organic binder content, offgassing is at a minimum.

Type

Paper manufactured from high temperature insulation wool.

Classification temperature

From 1100°C (2012°F) to 1300°C (2372°F)

The maximum continuous use temperature depends on the application. Unaffected by most chemicals except strong alkalis, phosphoric acid and molybdenum. For further advise please contact your local Morgan Advanced Materials representative.

Typical applications

- Industrial and domestic appliance gasketing
- Non-Ferrous ingot mould liners
- Aluminium transfer system back-up insulation
- Parting medium in induction furnaces
- Automotive heat shields

Benefits

- Low biopersistence
- Excellent thermal insulating performance
- Thin, flexible high temperature insulation
- Immune to thermal shock
- Low heat storage
- Easily die-cut to form complex shapes for high temperature gasketing
- Excellent tensile strength
- Low thermal conductivity
- Non-wetting to molten aluminium
- Superwool fibres are exonerated and are not classified as carcinogenic by IARC or under any national regulations on a global basis. They have no requirements for warning labels under GHS (Globally Harmonised System for the classification and labelling of chemicals). In Europe, Superwool fibres meet the requirements specified under NOTA Q of European Directive 67/548. All Superwool fibre products are therefore exempt from the classification and labelling regulation in Europe.



Data sheet

Superwool® Papers

Paper Product Name	Superwool Plus Paper	Superwool Plus Flex-Wrap	Superwool HT Paper
Fiber Class	AES	AES	AES
Physical Properties			
Manufacturing location	NA, EU, AS	NA	NA, EU, AS
Color	white	white	white
Continuous Use Temperature, °C (°F)	1000 (1832)	1000 (1832)	1200 (2192)
Classification Temperature, °C (°F)	1100 (2012)	1100 (2012)	1300 (2372)
Melting Temperature, °F	2327 (1275)	2327 (1275)	2552 (1400)
Density, kg/m ³ (pcf)	176-208 (11-13)	160-208 (10-13)	176-224 (11-14)
Tensile strength, Mpa (psi)	<0.45 (<65)	>0.17 (>25)	<0.35 (<50)
Permanent Linear Shrinkage, % ENV (1094-1)			
after 24hrs @ 1000°C (1832°F)	<2	-	-
after 24hrs @ 1260°C (2300°F)	-	-	<2
Chemical Analysis, % weight basis after firing			
Alumina, Al ₂ O ₃	trace	trace	trace
Silica, SiO ₂	60-70	60-70	70-80
Calcium oxide + Magnesium oxide, CaO + MgO	29-42	29-42	18-25
Other	1	1	<3
Loss of Ignition, LOI	5-10	2-5	5-10
Thermal Conductivity, W/m•K (BTU•in/hr•ft ²), per ASTM C201			
200°C (400°F)	-	-	0.04 (0.28)
260°C (500°F)	0.06 (0.39)	0.06 (0.39)	0.06 (0.39)
400°C (750°F)	-	-	0.07 (0.49)
538°C (1000°F)	0.06 (0.65)	0.06 (0.65)	0.06 (0.65)
600°C (1100°F)	-	-	0.1 (0.69)
816°C (1500°F)	0.15 (1.04)	0.15 (1.04)	0.15 (1.02)
982°C (1800°F)	0.19 (1.35)	0.19 (1.35)	-
1000°C (1832°F)	0.23 (1.6)	-	-
1100°C (2000°F)	-	-	0.22 (1.52)
1200°C (2200°F)	-	-	0.25 (1.73)

Contact

Europe:

Telephone:
+44 (0) 151 334 4030

E-mail:
marketing.tc@morganplc.com

North America:

Telephone:
+1 (706) 796 4200

E-mail:
northamerica.tc@morganplc.com

South America:

Telephone:
+54 (11) 4373 4439

E-mail:
marketing.tc@morganplc.com

Asia:

Telephone:
+65 6595 0000

E-mail:
asia.mc@morganplc.com

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

SUPERWOOL is a patented technology for high temperature insulation wools which have been developed to have a low bio persistence (information upon request). **SUPERWOOL** products may be covered by one or more of the following patents, or their foreign equivalents:

SUPERWOOL PLUS and **SUPERWOOL HT** products are covered by patent numbers:
US5714421 and US7470641, US7651965, US7875566, EP1544177 and EP1725503 respectively.

A list of foreign patent numbers is available upon request to Morgan Advanced Materials plc.

Morgan Advanced Materials plc Registered in England & Wales at Quadrant, 55-57 High Street, Windsor, Berkshire SL4 1LP UK Company No. 286773

Data sheet

Superwool® Papers

Availability and Packaging (Europe)

Superwool Plus and Superwool HT Paper are available in 500mm, 610mm, 1000mm and 1220mm wide rolls, packed in cartons. Non standard roll widths and lengths can also be supplied.

** Superwool Plus Paper only

Thickness, mm	Length, mm
0.5**	80
1	40
2	20
3	15
4	10
5	10
6	10
7	10
8	10
9	10
10	10

Availability and Packaging (North America)

Non standard roll widths and lengths can also be supplied.

	Thickness, in (mm)	Length, in (mm)	SqFt/Roll (SqM/Roll)	Mill Rolls Ft/Roll (Linear M/Roll)
Superwool Plus, Superwool Plus Flex-Wrap, Superwool HT	1/16 (1.6)	12 (305)	500 (46.6)	750 (229)
Superwool Plus, Superwool Plus Flex-Wrap, Superwool HT	1/16 (1.6)	24 (610)	500 (46.6)	750 (229)
	1/16 (1.6)	48 (1220)	500 (46.6)	750 (229)
Superwool Plus, Superwool Plus Flex-Wrap, Superwool HT	1/8 (3.2)	12 (305)	250 (23.2)	375 (114)
	1/8 (3.2)	24 (610)	250 (23.2)	375 (114)
Superwool Plus, Superwool Plus Flex-Wrap, Superwool HT	1/8 (3.2)	48 (1220)	250 (23.2)	375 (114)
	1/4 (6.4)	12 (305)	125 (11.6)	185 (56)
Superwool Plus, Superwool Plus Flex-Wrap, Superwool HT	1/4 (6.4)	24 (610)	125 (11.6)	185 (56)
	1/4 (6.4)	48 (1220)	125 (11.6)	185 (56)

Contact

Europe:

Telephone:
+44 (0) 151 334 4030

E-mail:
marketing.tc@morganplc.com

North America:

Telephone:
+1 (706) 796 4200

E-mail:
northamerica.tc@morganplc.com

South America:

Telephone:
+54 (11) 4373 4439

E-mail:
marketing.tc@morganplc.com

Asia:

Telephone:
+65 6595 0000

E-mail:
asia.mc@morganplc.com

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

SUPERWOOL is a patented technology for high temperature insulation wools which have been developed to have a low bio persistence (information upon request).

SUPERWOOL products may be covered by one or more of the following patents, or their foreign equivalents:

SUPERWOOL PLUS and **SUPERWOOL HT** products are covered by patent numbers:
US5714421 and US7470641, US7651965, US7875566, EP1544177 and EP1725503 respectively.

A list of foreign patent numbers is available upon request to Morgan Advanced Materials plc.

Morgan Advanced Materials plc Registered in England & Wales at Quadrant, 55-57 High Street, Windsor, Berkshire SL4 1LP UK Company No. 286773