

TECHNICAL DATA SHEET

GASKET SHEET PRO-160

SPECIFICATION				
Maximum operating pressure	MPa	4		
Maximum operating temperature	°C	continuous	180	
		peak	210	
Medium: water, gas, oil, alcohol, basic chemicals				
Technical features			wg normy	Acc. To test TP 62- 085-10
Density	g/cm³	1,7 - 2,1	DIN 28 090 -2	
Stability (16h/175°C)	MPa	20	DIN 52 913	
Compressibility	%	5 - 15	ASTM F 36 -J	
Minimum elastic relaxation	%	50	ASTM F 36 -J	
Specific amount of leakage	mg/sm	0,1	DIN 3535 - 6	
Resistance to liquids: thickness changes				
IRM 903 oil (5h/150°C) max	%	15	ASTM F 146	
ASTM liquid (5h/23°C)	%	15	ASTM F 146	
Flexibility	No cracks or gaps		ASTM F 147	
Colour and print	Green, printed on one side			
	DIN 28 091 – 2		FA-MA-1-0	
	ASTM F 104		F 712 111 M5	
Note:				
Parameters tested at 2mm thickness				

Acc. To
test TP 62-
085-10

PRO-HURT www.pro-hurt.pl DIN 28091-2 FA-MA-1-0 PRO-160 PN-EN ISO 9001	PRO-160 PN-EN ISO 9001	PRO-160 DIN 28091-2 FA-MA-1-0
PRO-HURT www.pro-hurt.pl DIN 28091-2 FA-MA-1-0 PRO-160 PN-EN ISO 9001	PRO-HURT PN-EN ISO 9001	PRO-160 DIN 28091-2 FA-MA-1-0
PRO-HURT www.pro-hurt.pl DIN 28091-2 FA-MA-1-0 PRO-160 PN-EN ISO 9001	PRO-HURT PN-EN ISO 9001	PRO-160 DIN 28091-2 FA-MA-1-0
PRO-HURT www.pro-hurt.pl DIN 28091-2 FA-MA-1-0 PRO-160 PN-EN ISO 9001	PRO-HURT PN-EN ISO 9001	PRO-160 DIN 28091-2 FA-MA-1-0



* This data sheet is confidential. Transmitting, copying and disclosing it to third parties requires the written consent of PRO-HURT. The present data sheet is directed at the addressee(s) referred to above and is the property of the addressee. Disclosure of the card is prohibited. If you are not the intended addressee, you must delete this document immediately and notify the sender by phone or email.