



# KLINGERSIL<sup>®</sup> C-4509 - premium high-pressure gasket able to withstand very high thermal and mechanical stresses.

Carbon fibers, special high temperature-resistant additives and an NBR bonding make up this special high-pressure high-pressure gasket. Its expanded metal reinforcement makes it capable of withstanding the highest thermal and mechanical stresses and high bolt loads. This gasket material is the first choice for the chemical industry, where it is mainly used in tandem with alkaline media and steam. The basic material KLINGERSIL® C-4500 is a Fire-Safe grade.

Basis composition	Carbon fibers and special high temperature-resistant additives bonded with NBR.				
Color	Black				
Certificates	DNV GL approval				

IKLINGERSIE		KLINGERS	
6.8209		C-4509	
CONCERNE AND INCLUMENT	IGERSIL CORLING	ERSIL	
	< @KLINGERSIL	KLINGERSIL	
		C-4509	
	SIL - COKLINGER		
KLINGER	KLINGERSIL		
5.4300		KUNGERSIL	
	C-1500	C-4509	
	COKLINGERSH.		
	80 6-4509		
KLINGERSIE		EM.	
C 4509	MGERSIL .	CI INTERNET	
	C-4509 EU		
		C-4509	
	KLINGERSIL		
		< KLIP	
	EU C-4509		
	GERSIL <sup>®</sup>	EU	
ALIM	GERSIL		
C-45			
		-4509	
NGERSIL		EL CONTRACTOR	
C-4509			
EU C-ASOP EU	C-4509	- CALING	
		C-450	
C-1500 CKLINGER	CII		
1-4300		FPSI	
ED 1-4309	RUNG		
	EU C-430	e	
		FU	

Sheet size	1000 x 1500 mm, 2000 x 1500 mm					
Thickness1.0 mm, 1.5 mm						
Tolerances	5					
Thickness	according to DIN 28091-1					
Length:	± 50 mm					
Width:	± 50 mm					


## Industry


General industry / Chemical / Oil & Gas / Energy / Pulp & Paper / Marine / Automotive

#### TECHNICAL DATA - Typical values for a thickness of 1.5 mm

Compressibility	ASTM F 36 J	%	10
Recovery	ASTM F 36 J	%	62
Stress relaxation DIN 52913	50 MPa, 16 h/300°C	MPa	43 41
Stress relaxation BS 7531	40 MPa, 16 h/300°C	MPa	
KLINGER cold/hot compression	thickness decrease at 23°C	%	8
50 MPa	thickness decrease at 300°C	%	6
Thickness increase after fluid	oil IRM 903: 5 h/150°C	%	3
immersion ASTM F 146	fuel B: 5 h/23°C	%	
Density		g/cm <sup>3</sup>	2.0
ASME-Code sealing factors			
for gasket thickness 1.5 mm	tightness class 0.1mg/s x m	MPa	y 30
			m 4.0







#### The tightness performance graph

The graph shows the required stress at assembling to seal a certain tightness class. The determination of the graph is based on EN13555 test procedure which applies 40bar Helium at room temperature. The sloping curve indicates the ability of the gasket to increase tightness with raising gasket stress.

## Chemical resistance chart

Simplified overview of the chemical resistance depending on the most important groups of raw materials:

KLINGERSIL® C-4509					A: sm	A: small or no attack		k till moderate att	tack (	C: strong attack	
Paraffinic hydrocarbon	Motor fuel	Aromates	Chlorinated hydrocarbon fluids	Motor oil	Mineral lubricants	Alcohol	Ketone	Ester	Water	Acid (diluted)	Base (diluted)
Α	В	С	С	Α	В	Α	С	С	Α	Α	Α

For more information on chemical resistance please visit www.klinger.co.at.

All information is based on years of experience in production and operation of sealing elements. However, in view of the wide variety of possible installation and operating conditions one cannot draw final conclusions in all application cases regarding the behaviour in gasket joint. The data may not, therefore, be used to support any warranty claims. This edition cancels all previous issues. Subject to change without notice.



Certified acc. to DIN EN ISO 9001:2015 Subject to technical alterations. Status: April 2020 Rich. Klinger Dichtungstechnik GmbH & Co KG / Am Kanal 8-10 / A-2352 Gumpoldskirchen, Austria Tel +43 (0) 2252/62599-137 / Fax +43 (0) 2252/62599-296 / e-mail: marketing@klinger.co.at

#### www.klinger.co.at